

# J-BAK2

$n_d = 1.539960$

$n_e = 1.542123$

$v_d = 59.52$

$v_e = 59.26$

Glass code (d)	540595
Glass code (e)	542593

Spectral l.	Refractive idx
2.058	1.51748
1.970	1.51862
1.530	1.52379
1.129	1.52829
1.064	1.52909
t	1.52976
s	1.53231
A'	1.534045
r	1.535627
C	1.537199
C'	1.537639
He-Ne	1.538049
D	1.539879
d	1.539960
e	1.542123
F	1.546271
F'	1.546787
g	1.551203
h	1.555299
0.389	1.557798
i	1.562285

Coef. disp. form. (pwr ser.)	
A0	2.33616060E+00
A1	-8.18245071E-03
A2	-9.82753897E-05
A3	1.27499096E-02
A4	1.22269251E-04
A5	8.48994057E-06
A6	-1.59525058E-07
A7	0.00000000E+00
A8	0.00000000E+00

Partial dispersion	
F-C	0.009072
F'-C'	0.009148
C-t	0.007438
C-A'	0.003154
d-C	0.002761
e-C	0.004924
g-d	0.011243
g-F	0.004932
h-g	0.004096
i-g	0.011082
C'-t	0.007878
e-C'	0.004484
F'-e	0.004664
i-F'	0.015498

Relative partial dispersion	
C-t/F-C	0.8199
C-A'/F-C	0.3477
d-C/F-C	0.3043
e-C/F-C	0.5428
g-d/F-C	1.2393
g-F/F-C	0.5437
h-g/F-C	0.4515
i-g/F-C	1.2216
C'-t/F'-C'	0.8612
e-C'/F'-C'	0.4902
F'-e/F'-C'	0.5098
i-F'/F'-C'	1.6941

Deviation of relative partial disp.	
Δ PdC	0.0003
Δ PgF	-0.0008

Specific gravity	2.84
------------------	------

Thermal properties	
CTE(-30,70) [1E-7/°C]	76
CTE(100,300) [1E-7/°C]	87
Tg [°C]	559
At [°C]	624
Ht condct. [W/m·K]	0.915
Sp. heat [kJ/kg·K]	0.632
Ht diffus. [1E-6 m2/sec]	0.508

Chemical properties [class]	
Acid res. (surface)	1
Alkaline detergent res.	2
Climate resistance	1
Water res. (powder)	2
Acid res. (powder)	2

Mechanical properties	
Knoop hardness	465 (5)
Abrasion hardness	119
Young's mod. [GPa]	70.7
Shear mod. [GPa]	28.7
Poisson's ratio	0.232
Stress optical coef. [1E-5 nm/cm/Pa]	2.80

Color Code (80%/5%)		330/295
Internal CC		324/292
Internal trans. (10mm)		
λ [nm]	T	
280	-	
290	0.03	
300	0.19	
310	0.48	
320	0.73	
330	0.87	
340	0.940	
350	0.971	
360	0.984	
365	0.988	
370	0.990	
380	0.990	
390	0.993	
400	0.996	
420	0.995	
440	0.994	
460	0.994	
480	0.995	
500	0.996	
550	0.996	
600	0.996	
650	0.995	
700	0.995	
800	0.992	
900	0.996	
1000	0.996	
1200	0.996	
1400	0.990	
1600	0.990	
1800	0.972	
2000	0.947	
2200	0.89	
2400	0.85	

Relative Δ n/Δ T [1E-6/°C]																
Temp. [°C]	1.083	t	s	A'	r	C	C'	He-Ne	d	e	F	F'	g	h	0.389	
80 to 90 (ref.)	1.6	1.6	1.7	1.9	2.0	2.1	2.1	2.1	2.2	2.4	2.7	2.8	3.1	3.5	3.7	
60 to 80 (ref.)	1.5	1.5	1.7	1.7	1.8	1.9	2.0	2.0	2.1	2.3	2.6	2.6	3.0	3.3	3.5	
40 to 60	1.4	1.4	1.5	1.6	1.7	1.8	1.8	1.9	2.0	2.1	2.4	2.5	2.8	3.1	3.3	
20 to 40	1.3	1.3	1.4	1.5	1.6	1.7	1.7	1.8	1.9	2.0	2.3	2.3	2.7	3.0	3.2	
0 to 20	1.2	1.3	1.4	1.5	1.5	1.6	1.7	1.7	1.8	1.9	2.2	2.2	2.6	2.9	3.0	
-20 to 0	1.2	1.3	1.4	1.4	1.5	1.6	1.6	1.7	1.8	1.9	2.2	2.2	2.5	2.8	3.0	
-40 to -20	1.3	1.3	1.4	1.5	1.6	1.7	1.7	1.7	1.8	1.9	2.2	2.2	2.5	2.8	2.9	
-60 to -40 (ref.)	1.4	1.5	1.6	1.6	1.7	1.8	1.8	1.8	1.9	2.0	2.3	2.3	2.6	2.9	3.0	
-70 to -60 (ref.)	1.6	1.6	1.7	1.8	1.9	1.9	2.0	2.0	2.1	2.2	2.4	2.5	2.7	3.0	3.1	

Absolute Δ n/Δ T [1E-6/°C]																
Temp. [°C]	1.083	t	s	A'	r	C	C'	He-Ne	d	e	F	F'	g	h	0.389	
80 to 90	0.6	0.7	0.8	0.9	1.0	1.1	1.1	1.2	1.3	1.4	1.7	1.8	2.2	2.5	2.7	
60 to 80	0.5	0.5	0.6	0.7	0.8	0.9	0.9	1.0	1.1	1.2	1.5	1.6	1.9	2.3	2.5	
40 to 60	0.2	0.3	0.4	0.5	0.5	0.6	0.7	0.7	0.8	0.9	1.2	1.3	1.6	1.9	2.1	
20 to 40	0.0	0.0	0.1	0.2	0.3	0.4	0.4	0.4	0.5	0.7	0.9	1.0	1.3	1.6	1.8	
0 to 20	-0.3	-0.2	-0.1	-0.1	0.0	0.1	0.1	0.1	0.3	0.4	0.6	0.7	1.0	1.3	1.5	
-20 to 0	-0.5	-0.5	-0.4	-0.3	-0.2	-0.2	-0.1	-0.1	0.0	0.1	0.4	0.4	0.7	0.9	1.1	
-40 to -20	-0.8	-0.7	-0.6	-0.6	-0.5	-0.4	-0.4	-0.4	-0.3	-0.2	0.1	0.1	0.4	0.6	0.8	
-60 to -40	-1.0	-1.0	-0.9	-0.8	-0.8	-0.7	-0.7	-0.7	-0.6	-0.5	-0.2	-0.2	0.1	0.3	0.4	
-70 to -60	-1.2	-1.2	-1.1	-1.0	-1.0	-0.9	-0.9	-0.9	-0.8	-0.7	-0.5	-0.4	-0.2	0.1	0.2	

Coef. disp. form. (frac. eq.) (ref.)	
P1	1.22545246E-01
Q1	9.24022804E+01
P2	1.79911705E-02
Q2	2.59658508E-02
P3	2.90195251E-01
Q3	5.32121925E-03

Fitting error of disp. form. σ [1E-6]		
	Visible	Infrared
Power ser. eq.	0.5	7.5
Frac. eq. (ref.)	0.7	7.5

Prod. Freq. (A to F)	D
----------------------	---

Similar glass type			
OHARA	S-BAL12	HOYA	-
CDGM	H-BaK2	SCHOTT	N-BAK2

2015-4-1	Color Code
2009-9-1	1st edition