

J-LAK7

$n_d = 1.651600$

$n_e = 1.654253$

$v_d = 58.57$

$v_e = 58.34$

Glass code (d)
652586
Glass code (e)
654583

Spectral l.	Refractive idx
2.058	1.62263
1.970	1.62418
1.530	1.63114
1.129	1.63704
1.064	1.63808
t	1.63893
s	1.64215
A'	1.644307
r	1.646266
C	1.648206
C'	1.648747
He-Ne	1.649252
D	1.651501
d	1.651600
e	1.654253
F	1.659331
F'	1.659962
g	1.665356
h	1.670353
0.389	1.673398
i	1.678861

Coef. disp. form. (pwr ser.)	
A0	2.68232720E+00
A1	-1.19713031E-02
A2	-1.43724360E-04
A3	1.64555463E-02
A4	2.17295781E-04
A5	4.69383509E-06
A6	3.49394854E-08
A7	0.00000000E+00
A8	0.00000000E+00

Partial dispersion	
F-C	0.011125
F'-C'	0.011215
C-t	0.009279
C-A'	0.003899
d-C	0.003394
e-C	0.006047
g-d	0.013756
g-F	0.006025
h-g	0.004997
i-g	0.013505
C'-t	0.009820
e-C'	0.005506
F'-e	0.005709
i-F'	0.018899

Relative partial dispersion	
C-t/F-C	0.8341
C-A'/F-C	0.3505
d-C/F-C	0.3051
e-C/F-C	0.5436
g-d/F-C	1.2365
g-F/F-C	0.5416
h-g/F-C	0.4492
i-g/F-C	1.2139
C'-t/F'-C'	0.8756
e-C'/F'-C'	0.4909
F'-e/F'-C'	0.5091
i-F'/F'-C'	1.6852

Deviation of relative partial disp.	
ΔPdC	0.0014
ΔPgF	-0.0045

Internal CC (80%/5%)	
333/262	

Color Code (80%/5%)	
350/265	

CCI	
B	0.00
G	0.24
R	0.22

Thermal properties	
CTE(-30,70) [1E-7/°C]	66
CTE(100,300) [1E-7/°C]	82
Tg [°C]	651
At [°C]	681
Ht condct. [W/m·K]	0.953
Sp. heat [kJ/kg·K]	0.670
Ht diffus. [1E-6 m2/sec]	0.431

Chemical properties [class]	
Acid res. (surface)	5
Alkaline detergent res.	4
Climate resistance	1
Water res. (powder)	3
Acid res. (powder)	5

Mechanical properties	
Knoop hardness	583 (6)
Abrasion hardness	106
Young's mod. [GPa]	100.3
Shear mod. [GPa]	39.0
Poisson's ratio	0.285
Stress optical coef. [1E-5 nm/cm/Pa]	2.02

Internal trans. (10mm)		
λ [nm]	τ	
280	0.17	
290	0.28	
300	0.40	
310	0.53	
320	0.66	
330	0.77	
340	0.85	
350	0.907	
360	0.944	
370	0.966	
380	0.978	
390	0.985	
400	0.989	
420	0.992	
440	0.994	
460	0.995	
480	0.997	
500	0.998	
550	0.998	
600	0.998	
650	0.998	
700	0.998	
800	0.998	
900	0.997	
1000	0.997	
1200	0.996	
1400	0.993	
1600	0.990	
1800	0.981	
2000	0.963	
2200	0.900	
2400	0.70	

Specific gravity	
3.3	

Relative $\Delta n / \Delta T$ [1E-6/°C]																
Temp. [°C]	1.083	t	s	A'	r	C	C'	He-Ne	d	e	F	F'	g	h	0.389	
80 to 90 (ref.)	2.0	2.1	2.1	2.3	2.4	2.5	2.6	2.6	2.7	2.9	3.2	3.3	3.7	4.0	4.3	
60 to 80 (ref.)	1.9	2.0	2.1	2.2	2.3	2.4	2.4	2.5	2.6	2.8	3.1	3.2	3.5	3.9	4.1	
40 to 60	1.8	1.8	2.0	2.1	2.2	2.3	2.3	2.3	2.5	2.6	3.0	3.0	3.3	3.7	3.9	
20 to 40	1.7	1.8	1.9	2.0	2.1	2.2	2.2	2.2	2.4	2.5	2.8	2.9	3.2	3.5	3.7	
0 to 20	1.7	1.7	1.8	1.9	2.0	2.1	2.1	2.2	2.3	2.4	2.7	2.8	3.1	3.4	3.6	
-20 to 0	1.7	1.7	1.8	1.9	2.0	2.1	2.1	2.1	2.3	2.4	2.7	2.7	3.0	3.3	3.5	
-40 to -20	1.7	1.8	1.9	1.9	2.0	2.1	2.2	2.2	2.3	2.4	2.7	2.7	3.0	3.3	3.5	
-60 to -40 (ref.)	1.9	1.9	2.0	2.1	2.2	2.3	2.3	2.3	2.4	2.6	2.8	2.9	3.1	3.4	3.6	
-70 to -60 (ref.)	2.1	2.1	2.2	2.3	2.4	2.5	2.5	2.5	2.6	2.8	3.0	3.0	3.3	3.6	3.7	

Absolute $\Delta n / \Delta T$ [1E-6/°C]																
Temp. [°C]	1.083	t	s	A'	r	C	C'	He-Ne	d	e	F	F'	g	h	0.389	
80 to 90	1.0	1.1	1.2	1.3	1.4	1.5	1.5	1.6	1.7	1.9	2.2	2.2	2.6	3.0	3.2	
60 to 80	0.8	0.9	1.0	1.1	1.2	1.3	1.3	1.3	1.5	1.7	2.0	2.0	2.4	2.7	2.9	
40 to 60	0.6	0.6	0.7	0.8	0.9	1.0	1.0	1.1	1.2	1.4	1.7	1.7	2.0	2.4	2.6	
20 to 40	0.3	0.3	0.4	0.5	0.6	0.7	0.8	0.8	0.9	1.1	1.4	1.4	1.7	2.0	2.2	
0 to 20	0.1	0.1	0.2	0.3	0.4	0.5	0.5	0.5	0.6	0.8	1.1	1.1	1.4	1.7	1.9	
-20 to 0	-0.2	-0.2	-0.1	0.0	0.1	0.2	0.2	0.2	0.3	0.5	0.7	0.8	1.1	1.3	1.5	
-40 to -20	-0.5	-0.4	-0.4	-0.3	-0.2	-0.1	-0.1	-0.1	0.1	0.2	0.4	0.5	0.7	1.0	1.2	
-60 to -40	-0.7	-0.7	-0.6	-0.5	-0.5	-0.4	-0.4	-0.3	-0.2	-0.1	0.1	0.2	0.4	0.7	0.8	
-70 to -60	-0.9	-0.9	-0.8	-0.7	-0.7	-0.6	-0.6	-0.5	-0.4	-0.3	-0.1	-0.1	0.2	0.4	0.6	

Coef. disp. form. (frac. eq.) (ref.)	
P1	1.23367890E-01
Q1	7.50281422E+01
P2	7.86744637E-02
Q2	1.56987933E-02
P3	2.80638114E-01
Q3	3.60652473E-03

Fitting error of disp. form. σ [1E-6]		
	Visible	Infrared
Power ser. eq.	0.4	2.9
Frac. eq. (ref.)	0.4	3.1

Prod. Freq. (A to D)	C
----------------------	---

Similar glass type			
OHARA	S-LAL7	HOYA	LAC7
CDGM	H-LaK50A	SCHOTT	N-LAK7

2019-4-1	Transmittance
2018-4-1	Prod. Freq.
2015-4-1	Color Code, Prod. Freq.