

# J-LASF015

$n_d = 1.804000$

$n_e = 1.808106$

$v_d = 46.60$

$v_e = 46.35$

Glass code (d)	804466
Glass code (e)	808464

Spectral l.	Refractive idx
2.058	1.76695
1.970	1.76858
1.530	1.77612
1.129	1.78310
1.064	1.78442
t	1.78553
s	1.78994
A'	1.793033
r	1.795917
C	1.798824
C'	1.799643
He-Ne	1.800408
D	1.803847
d	1.804000
e	1.808106
F	1.816078
F'	1.817079
g	1.825697
h	1.833795
0.389	1.838784
i	1.847835

Coef. disp. form. (pwr ser.)	
A0	3.17452404E+00
A1	-1.32156517E-02
A2	-1.65919934E-04
A3	2.76472367E-02
A4	4.83338934E-04
A5	1.20380702E-05
A6	6.02649728E-07
A7	0.00000000E+00
A8	0.00000000E+00

Partial dispersion	
F-C	0.017254
F'-C'	0.017436
C-t	0.013293
C-A'	0.005791
d-C	0.005176
e-C	0.009282
g-d	0.021697
g-F	0.009619
h-g	0.008098
i-g	0.022138
C'-t	0.014112
e-C'	0.008463
F'-e	0.008973
i-F'	0.030756

Relative partial dispersion	
C-t/F-C	0.7704
C-A'/F-C	0.3356
d-C/F-C	0.3000
e-C/F-C	0.5380
g-d/F-C	1.2575
g-F/F-C	0.5575
h-g/F-C	0.4693
i-g/F-C	1.2831
C'-t/F'-C'	0.8094
e-C'/F'-C'	0.4854
F'-e/F'-C'	0.5146
i-F'/F'-C'	1.7639

Deviation of relative partial disp.	
$\Delta PdC$	0.0018
$\Delta PgF$	-0.0087

Internal CC (80%/5%)	
355/312	

Color Code (80%/5%)	
385/315	

CCI	
B	0.00
G	0.53
R	0.54

Thermal properties	
CTE(-30,70) [1E-7/°C]	60
CTE(100,300) [1E-7/°C]	75
Tg [°C]	697
At [°C]	728
Ht condct. [W/m·K]	0.834
Sp. heat [kJ/kg·K]	0.470
Ht diffus. [1E-6 m2/sec]	0.387

Chemical properties [class]	
Acid res. (surface)	1
Alkaline detergent res.	1
Climate resistance	1
Water res. (powder)	1
Acid res. (powder)	3

Mechanical properties	
Knoop hardness	670 (7)
Abrasion hardness	64
Young's mod. [GPa]	119.6
Shear mod. [GPa]	46.1
Poisson's ratio	0.298
Stress optical coef. [1E-5 nm/cm/Pa]	1.43

Internal trans. (10mm)	
$\lambda$ [nm]	$\tau$
280	0.00
290	0.00
300	0.00
310	0.03
320	0.16
330	0.39
340	0.60
350	0.75
360	0.85
370	0.907
380	0.942
390	0.962
400	0.975
420	0.985
440	0.989
460	0.992
480	0.995
500	0.996
550	0.998
600	0.998
650	0.998
700	0.999
800	0.997
900	0.995
1000	0.996
1200	0.998
1400	0.997
1600	0.993
1800	0.986
2000	0.969
2200	0.923
2400	0.74

Specific gravity	
4.57	

Relative $\Delta n / \Delta T$ [1E-6/°C]															
Temp. [°C]	1.083	t	s	A'	r	C	C'	He-Ne	d	e	F	F'	g	h	0.389
80 to 90 (ref.)	3.5	3.6	3.8	4.0	4.1	4.3	4.4	4.4	4.7	5.0	5.6	5.6	6.3	6.9	7.4
60 to 80 (ref.)	3.4	3.5	3.7	3.9	4.0	4.2	4.2	4.3	4.5	4.8	5.4	5.5	6.1	6.8	7.3
40 to 60	3.3	3.4	3.6	3.7	3.9	4.1	4.1	4.2	4.4	4.7	5.3	5.3	5.9	6.6	7.0
20 to 40	3.2	3.3	3.5	3.7	3.8	4.0	4.0	4.1	4.3	4.6	5.1	5.2	5.8	6.4	6.8
0 to 20	3.2	3.3	3.5	3.6	3.7	3.9	3.9	4.0	4.2	4.5	5.0	5.1	5.7	6.2	6.7
-20 to 0	3.2	3.3	3.5	3.6	3.7	3.9	3.9	4.0	4.2	4.5	5.0	5.1	5.6	6.2	6.6
-40 to -20	3.3	3.4	3.6	3.7	3.8	4.0	4.0	4.1	4.3	4.5	5.0	5.1	5.6	6.2	6.6
-60 to -40 (ref.)	3.5	3.6	3.8	3.9	4.0	4.1	4.2	4.2	4.4	4.7	5.2	5.2	5.7	6.3	6.7
-70 to -60 (ref.)	3.7	3.8	4.0	4.1	4.2	4.4	4.4	4.4	4.6	4.9	5.4	5.4	5.9	6.4	6.8

Absolute $\Delta n / \Delta T$ [1E-6/°C]															
Temp. [°C]	1.083	t	s	A'	r	C	C'	He-Ne	d	e	F	F'	g	h	0.389
80 to 90	2.4	2.5	2.7	2.9	3.0	3.2	3.2	3.3	3.5	3.8	4.4	4.5	5.1	5.8	6.3
60 to 80	2.2	2.3	2.5	2.7	2.8	3.0	3.0	3.1	3.3	3.6	4.2	4.2	4.9	5.5	6.0
40 to 60	1.9	2.0	2.2	2.4	2.5	2.7	2.7	2.8	3.0	3.3	3.9	3.9	4.5	5.1	5.6
20 to 40	1.7	1.8	2.0	2.1	2.2	2.4	2.4	2.5	2.7	3.0	3.5	3.6	4.2	4.7	5.2
0 to 20	1.4	1.5	1.7	1.8	2.0	2.1	2.2	2.2	2.4	2.7	3.2	3.3	3.8	4.4	4.8
-20 to 0	1.2	1.2	1.4	1.6	1.7	1.8	1.9	1.9	2.1	2.4	2.9	2.9	3.5	4.0	4.4
-40 to -20	0.9	1.0	1.2	1.3	1.4	1.5	1.6	1.6	1.8	2.1	2.5	2.6	3.1	3.6	4.0
-60 to -40	0.6	0.7	0.9	1.0	1.1	1.2	1.3	1.3	1.5	1.8	2.2	2.3	2.7	3.2	3.6
-70 to -60	0.4	0.5	0.7	0.8	0.9	1.0	1.1	1.1	1.3	1.5	2.0	2.0	2.5	3.0	3.3

Coef. disp. form. (frac. eq.) (ref.)	
P1	1.10686191E-01
Q1	7.43053260E+01
P2	2.71367682E-02
Q2	3.09494207E-02
P3	3.93128419E-01
Q3	5.72630320E-03

Fitting error of disp. form. $\sigma$ [1E-6]		
	Visible	Infrared
Power ser. eq.	0.8	3.9
Frac. eq. (ref.)	0.9	4.0

Prod. Freq. (A to D)	A
----------------------	---

Similar glass type			
OHARA	S-LAH65V	HOYA	TAF3
CDGM	H-ZLaF50D	SCHOTT	N-LASF44

2019-4-1	Transmittance
2015-4-1	Internal trans, Color Code, Similar glass type
2009-9-1	1st edition