

# J-SF6HS

$n_d = 1.805180$

$n_e = 1.812633$

$v_d = 25.45$

$v_e = 25.24$

Glass code (d)	805255
Glass code (e)	813252

Spectral l.	Refractive idx
2.058	1.75397
1.970	1.75551
1.530	1.76319
1.129	1.77161
1.064	1.77341
t	1.77497
s	1.78153
A'	1.786439
r	1.791185
C	1.796109
C'	1.797519
He-Ne	1.798846
D	1.804907
d	1.805180
e	1.812633
F	1.827749
F'	1.829709
g	1.847229
h	1.864867
0.389	1.876421
i	-

Coef. disp. form. (pwr ser.)	
A0	3.11993645E+00
A1	-1.26679163E-02
A2	0.00000000E+00
A3	4.21698355E-02
A4	3.04768926E-03
A5	-4.20720196E-04
A6	1.06770582E-04
A7	-1.09382035E-05
A8	5.57077794E-07

Partial dispersion	
F-C	0.031640
F'-C'	0.032190
C-t	0.021142
C-A'	0.009670
d-C	0.009071
e-C	0.016524
g-d	0.042049
g-F	0.019480
h-g	0.017638
i-g	-
C'-t	0.022552
e-C'	0.015114
F'-e	0.017076
i-F'	-

Relative partial dispersion	
C-t/F-C	0.6682
C-A'/F-C	0.3056
d-C/F-C	0.2867
e-C/F-C	0.5223
g-d/F-C	1.3290
g-F/F-C	0.6157
h-g/F-C	0.5575
i-g/F-C	-
C'-t/F'-C'	0.7006
e-C'/F'-C'	0.4695
F'-e/F'-C'	0.5305
i-F'/F'-C'	-

Deviation of relative partial disp.	
$\Delta PdC$	-0.0020
$\Delta PgF$	0.0140

Internal CC (80%/5%)	
390/361	

Color Code (80%/5%)	
425/360	

CCI	
B	0.00
G	2.25
R	2.36

Thermal properties	
CTE(-30,70) [1E-7/°C]	86
CTE(100,300) [1E-7/°C]	110
Tg [°C]	571
At [°C]	611
Ht condct. [W/m·K]	1.070
Sp. heat [kJ/kg·K]	0.662
Ht diffus. [1E-6 m2/sec]	0.484

Chemical properties [class]	
Acid res. (surface)	1
Alkaline detergent res.	1
Climate resistance	1
Water res. (powder)	2
Acid res. (powder)	1

Mechanical properties	
Knoop hardness	482 (5)
Abrasion hardness	182
Young's mod. [GPa]	92.9
Shear mod. [GPa]	36.7
Poisson's ratio	0.264
Stress optical coef. [1E-5 nm/cm/Pa]	2.95

Internal trans. (10mm)	
$\lambda$ [nm]	$\tau$
280	0.00
290	0.00
300	0.00
310	0.00
320	0.00
330	0.00
340	0.00
350	0.00
360	0.04
370	0.26
380	0.58
390	0.80
400	0.89
420	0.949
440	0.972
460	0.982
480	0.987
500	0.991
550	0.997
600	0.998
650	0.999
700	0.999
800	0.999
900	0.999
1000	0.998
1200	0.997
1400	0.993
1600	0.987
1800	0.973
2000	0.962
2200	0.929
2400	0.88

Specific gravity	
3.34	

Relative $\Delta n / \Delta T$ [1E-6/°C]																
Temp. [°C]	1.083	t	s	A'	r	C	C'	He-Ne	d	e	F	F'	g	h	0.389	
80 to 90 (ref.)	-0.7	-0.6	-0.3	0.0	0.3	0.7	0.8	0.9	1.4	2.1	3.6	3.8	5.9	8.5	10.7	
60 to 80 (ref.)	-0.9	-0.7	-0.4	-0.1	0.2	0.5	0.6	0.7	1.2	1.9	3.3	3.5	5.5	8.1	10.2	
40 to 60	-1.0	-0.9	-0.5	-0.3	0.0	0.3	0.4	0.5	1.0	1.6	3.0	3.2	5.1	7.5	9.4	
20 to 40	-1.1	-1.0	-0.7	-0.4	-0.1	0.2	0.3	0.4	0.8	1.4	2.7	2.9	4.7	6.9	8.7	
0 to 20	-1.2	-1.0	-0.7	-0.5	-0.3	0.0	0.1	0.2	0.7	1.2	2.5	2.6	4.3	6.4	8.1	
-20 to 0	-1.2	-1.1	-0.8	-0.5	-0.3	0.0	0.1	0.1	0.6	1.1	2.3	2.4	4.0	5.9	7.5	
-40 to -20	-1.1	-1.0	-0.7	-0.5	-0.3	0.0	0.1	0.1	0.5	1.0	2.1	2.3	3.7	5.5	7.0	
-60 to -40 (ref.)	-0.9	-0.8	-0.6	-0.4	-0.2	0.1	0.2	0.2	0.6	1.1	2.1	2.2	3.6	5.2	6.6	
-70 to -60 (ref.)	-0.7	-0.6	-0.4	-0.2	0.0	0.3	0.3	0.4	0.8	1.2	2.2	2.3	3.6	5.1	6.3	

Absolute $\Delta n / \Delta T$ [1E-6/°C]																
Temp. [°C]	1.083	t	s	A'	r	C	C'	He-Ne	d	e	F	F'	g	h	0.389	
80 to 90	-1.8	-1.7	-1.4	-1.1	-0.8	-0.4	-0.3	-0.2	0.3	1.0	2.5	2.7	4.7	7.4	9.5	
60 to 80	-2.1	-1.9	-1.6	-1.3	-1.0	-0.7	-0.6	-0.5	0.0	0.7	2.1	2.3	4.3	6.8	8.9	
40 to 60	-2.3	-2.2	-1.9	-1.6	-1.4	-1.0	-0.9	-0.9	-0.4	0.2	1.6	1.8	3.7	6.0	8.0	
20 to 40	-2.6	-2.5	-2.2	-2.0	-1.7	-1.4	-1.3	-1.2	-0.8	-0.2	1.1	1.3	3.0	5.2	7.1	
0 to 20	-2.9	-2.8	-2.5	-2.3	-2.0	-1.7	-1.7	-1.6	-1.1	-0.6	0.6	0.8	2.4	4.5	6.2	
-20 to 0	-3.2	-3.1	-2.8	-2.6	-2.4	-2.1	-2.0	-1.9	-1.5	-1.0	0.1	0.3	1.8	3.7	5.3	
-40 to -20	-3.5	-3.4	-3.1	-2.9	-2.6	-2.5	-2.4	-2.3	-1.9	-1.4	-0.4	-0.2	1.2	2.9	4.4	
-60 to -40	-3.8	-3.7	-3.4	-3.2	-3.0	-2.8	-2.7	-2.7	-2.3	-1.8	-0.9	-0.7	0.6	2.2	3.5	
-70 to -60	-4.0	-3.9	-3.7	-3.5	-3.3	-3.1	-3.0	-2.9	-2.6	-2.2	-1.2	-1.1	0.1	1.6	2.8	

Coef. disp. form. (frac. eq.) (ref.)	
P1	1.01435791E-01
Q1	7.59148418E+01
P2	2.72714884E-02
Q2	6.17300189E-02
P3	3.86525039E-01
Q3	8.91225912E-03

Fitting error of disp. form. $\sigma$ [1E-6]		
	Visible	Infrared
Power ser. eq.	0.9	3.7
Frac. eq. (ref.)	3.3	11.4

Prod. Freq. (A to D)	A
----------------------	---

Similar glass type			
OHARA	S-TIH6	HOYA	FD60-W
CDGM	H-ZF7LAGT	SCHOTT	N-SF6HT

2019-4-1	Transmittance
2018-4-1	Young's mod., Shear mod., Similar glass type
2016-4-1	Similar glass type